

PROPERTIES	ASTM TEST NO.	UNITS	450G
Tensile Strength	D 638	KPSI	14.50
Elongation at Break	D 638	%	50.00
Flexural Modulus	D 790	KPSI	594.50
Flexural Strength	D 790	KPSI	24.60
Shear Strength	D 3846	KPSI	7.70
Compressive Strength	D 695	KPSI	17.10
Izod Impact Notched	D 256	FT-LB/IN.	1.57
UL Continous Use Temp.	UL746B	F	482.00
Water Absorption @ 24 hrs.	D 570	5	0.05

We believe this information is the best currently available on the subject. It is subject to revision as additional knowledge and experience are gained. A.L. Hyde Company makes no guarantee of results and assumes no obligation of liability whatsoever in connection with this information. Anyone intending to use recommendations contained in this publication should first satisfy himself that the recommendations are suitable for his use and meet all appropriate safety and health standards. This publication is not a license to operate under, or intended to suggest infringement of any existing patents. References to products not of A.L. Hyde manufacture do not indicate endorsement of named products or unsuitability of other similar products.

For more information contact A.L. Hyde Company, or your local distributor of Hyde quality engineering thermoplastics.

Your local distributor:

ALH18695